



# Ultrafuse® PPSU

## Welcome to the World of High Temperature Stable Applications!

Ultrafuse® PPSU was specially developed for FFF printing based on BASF's advanced Ultrason® materials. The Ultrason® resins are amorphous thermoplastics derived from polyethersulfone (PESU), polysulfone (PSU) and polyphenylsulfone (PPSU) and ensure very high thermal resistance.

With its wide spectrum of material performance advantages, Ultrafuse® PPSU can be successfully used in applications where other plastics, e.g. polyamide, polycarbonate, polyoxymethylene and polyalkylene terephthalates, fail to meet the performance specifications. With its inherent flame-retardant properties, it is an especially suitable material for the aerospace industry.

### Benefits at a Glance

- Inherently flame retardant
- Short-term temperature resistance up to 220 °C
- Resistant to long-term service temperatures up to 180 °C
- High dimensional stability
- Creep strength at high temperatures
- Resistant to hot water and coolants
- Oil-resistant, even at temperatures up to 170 °C
- Fuel and fluorine resistant

### Example Applications

- Suitable for autoclaving processes
- Aerospace industry
- All applications exposed to high temperatures

### Material Properties

<b>Tensile Strength (MPa)</b>	51.6 (ZX), 65.10 (XY)
<b>Flexural Modulus (MPa)</b>	1999 (ZX), 2152 (XY)
<b>Elongation at Break</b>	3.2% (ZX), 6.5% (XY)
<b>Impact Strength Izod notched (kJ/m<sup>2</sup>)</b>	5.5 (ZX), 12.0 (XY)
<b>Impact Strength Izod unnotched (kJ/m<sup>2</sup>)</b>	14.3 (ZX), 119.0 (XY)
<b>HDT @ 0.45 MPa</b>	218 °C

### Printing Guidelines

<b>Nozzle Temperature</b>	390-410 °C
<b>Build Chamber Temperature</b>	170-210 °C
<b>Bed Temperature</b>	220 °C
<b>Bed Material</b>	BASF fiber-reinforced build sheet
<b>Nozzle Diameter</b>	≥ 0.4 mm
<b>Print Speed</b>	25-50 mm / s

The product data is provided in good faith and represents typical properties based on our current knowledge and experience; these data are not to be construed as specification limits or minimum values. Product properties may be changed without notice. This document does not create any liability, warranty or guarantee of product performance. It is the buyer's responsibility to determine the suitability of Ultrafuse® products for the intended application.



# Ultrafuse® PPSU

