



# **BEDROCK 3D PP GF30**

Glass Fiber Reinforced. UV-Resistant. Industrial-Grade. Durable.

## **Technical Documentation Sheet**

version 1.0





## Technical Data Sheet

### PP GF30

Glass Fiber Reinforced. UV-Resistant. Industrial-Grade. Durable.

BEDROCK 3D PP GF30 takes polypropylene to the next level with 30% glass fiber reinforcement, combining toughness, chemical resistance, and long-term durability in one high-performance filament. Designed for demanding environments, it's the perfect match for automotive, outdoor, and industrial applications where unfilled PP just isn't enough.

#### Filament Properties

Filament Diameter	1.75 mm	2.85 mm
Average diameter Tolerance	±0.050 mm	±0.1 mm
Average ovality	<0.050 mm	<0.050 mm
Available Spool size	700 g, 2.2 kg	700 g, 2.2 kg
Available colors	black	

#### Spool Properties

Spool size	750 g	2.0 kg	4.0 kg	8.0 kg
Outer diameter	200 mm	300 mm	350 mm	355 mm
Inner diameter	50.5 mm	51.5 mm	51.7 mm	36 mm
Width	55 mm	103 mm	103 mm	167 mm

#### Recommended 3D-Print processing parameters

#### Used for test specimens

Printer	FFF printer	Ultimaker S5
Nozzle Temperature <sup>1)</sup>	240 – 260°C	280 °C
Build Chamber Temperature	-	Passively heated (cover)
Bed Temperature	20 – 40°C	90 °C

<sup>1</sup> Fast printing might require an additional increase of the nozzle temperature; the stated printing speed is based on current validations. As equipment and technology continues to evolve, it is possible that even higher printing speeds may be attainable in the future.



Bed Material	PP GF adhesive or PP tape	Glass + Magigoo PPGF
Nozzle Diameter	$\geq 0.6$ mm	0.6 mm
Print Speed	30 - 80 mm/s	40 mm/s
Max Volumetric Speed <sup>2)</sup>	16 mm <sup>3</sup> /s	//

Please check your standard and/or high speed print profile availability for an easy start at [www.bedrock3d.com](http://www.bedrock3d.com).

---

<sup>2</sup> Based on Bambu Lab X1C with a nozzle diameter of 0.6 mm



## Further Recommendations

Drying recommendations to ensure printability and best mechanical properties<sup>3)</sup>

Support material compatibility	Single material breakaway
--------------------------------	---------------------------

Warehousing

BEDROCK 3D PP GF30 filament should be stored at 15 - 25°C in its originally sealed package in a clean and dry environment. If the recommended storage conditions are observed the products will have a minimum shelf life of 12 months.

General Properties	Standard	Average Values
Filament Density <sup>4)</sup>	ISO 1183-1	1036 kg/m <sup>3</sup>

Tensile Properties <sup>5)</sup>	Standard	Average Values		
		XY-Direction	XZ-Direction	ZX-Direction
Tensile strength <sup>6)</sup>	ISO 527	41.7 MPa	-	15.9 MPa
Elongation at Break <sup>6)</sup>	ISO 527	4.4 %	-	0.8 %
Young's Modulus <sup>7)</sup>	ISO 527	2628 MPa	-	2242 MPa

<sup>3</sup> Please note: To ensure constant material properties the material should always be kept dry.

<sup>4</sup> measured on filament

<sup>5</sup> Samples were conditioned in standard climate (23°C, 50% RH 72h)

<sup>6</sup> Testing speed: 5 mm/min

<sup>7</sup> Testing speed: 1 mm/min



Flexural Properties <sup>6) 8)</sup>	Standard	Average Values		
		XY- Direction	XZ- Direction	ZX- Direction

Flexural Strength	ISO 178	76.8 MPa	95.3 MPa	19.3 MPa
-------------------	---------	----------	----------	----------

Flexural Modulus	ISO 178	3507 MPa	4026 MPa	1671 MPa
------------------	---------	----------	----------	----------

Flexural Elongation at Break	ISO 178	4.6 %	3.3 %	1.3 %
------------------------------	---------	-------	-------	-------

Impact Properties <sup>6)</sup>	Standard	Average Values		
		XY- Direction	XZ- Direction	ZX- Direction

Impact Strength Charpy (notched)	ISO 179-2	5.3 kJ/m <sup>2</sup>	5.2 kJ/m <sup>2</sup>	1.2 kJ/m <sup>2</sup>
----------------------------------	-----------	-----------------------	-----------------------	-----------------------

Impact Strength Charpy (unnotched)	ISO 179-2	23.1 kJ/m <sup>2</sup>	25.8 kJ/m <sup>2</sup>	2.5 kJ/m <sup>2</sup>
------------------------------------	-----------	------------------------	------------------------	-----------------------

Impact Strength Izod (notched)	ISO 180	5.6 kJ/m <sup>2</sup>	6.2 kJ/m <sup>2</sup>	1.4 kJ/m <sup>2</sup>
--------------------------------	---------	-----------------------	-----------------------	-----------------------

Impact Strength Izod (unnotched)	ISO 180	20.5 kJ/m <sup>2</sup>	2.4 kJ/m <sup>2</sup>	2.6 kJ/m <sup>2</sup>
----------------------------------	---------	------------------------	-----------------------	-----------------------

Thermal Properties <sup>6)</sup>	Standard	Average Values
HDT A at 1.8 MPa	ISO 75-2	117 °C
HDT B at 0.45 MPa	ISO 75-2	148 °C
Vicat softening point at 50 N	ISO 306	138 °C
Vicat softening point at 10 N	ISO 306	164 °C
Crystallization Temperature		125 °C
Glass Transition Temperature	ISO 11357-2	-5 °C
Melting Temperature	ISO 11357-3	158 °C
Melt Volume-Flow Rate (MVR)	ISO 1133	11.7 cm <sup>3</sup> /10 min (220°C, 2,16 kg)


<sup>8</sup> Testing speed: 2 mm/min  
Measured on milled specimens



Hardness and Abrasion	Standard	Typical Values
Shore Hardness D (15s)	DIN ISO 7619-1	73

### Print direction explanation

The orientation of the 3D printed part in the printer is always aligned with the longest axis first. The print direction is consistently along the Z-axis.





The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. Values in this document are average values, measured and calculated according to the instructions in the listed standards. The used specimens are produced with the Fused Filament Fabrication method. Measured values can vary depending on used print orientation and print parameters.

Please contact us for further product information, like for example REACH, RoHS, FCS.

The safety data given in this publication is for informational purposes only and does not constitute a legally binding MSDS. The relevant MSDS can be obtained upon request from your supplier or you may contact Forward AM Technologies Netherlands B.V. directly at [customerservice@bedrock3d.com](mailto:customerservice@bedrock3d.com)

Process materials in a well-ventilated room, or use professional extraction systems.